



Rapid Surface Repair Easy Mix™

Fast Turnaround Surface Repair for Roads, Runways & Bridges

PRODUCT DESCRIPTION

Five Star® Rapid Surface Repair Easy Mix is a self-leveling, low viscosity, two-part liquid polyurethane-hybrid polymer. When supplemented with its proprietary blended aggregate, this product is used to repair and rehabilitate concrete and asphaltic concrete pavements. The enhanced polymer is high performance, rapid setting, and can be used to make an impact and traffic resistant polymer concrete that can be used at temperatures down to 0°F (-18°C). Within minutes of placement, durable, long-lasting repairs are able to handle vibration, heavy traffic, and thermal movement.

ADVANTAGES

- No priming required to bond to concrete, asphalt, steel or wood
- Waterproof, chemically resistant membrane protects substrates from freeze-thaw spalling
- Use neat or with aggregate
- Stops further corrosion of reinforcing steel
- Traffic ready in as little as 30 minutes*
- Very low odor
- Make repairs year round — can be used in temperatures down to 0°F (-18°C)

USES

- Expansion joint and bridge header reconstruction
- Control joint filler
- Repair cracks, potholes, spalls
- Airport runways, walkways, floors, and parking lots
- Airport lighting cans and conduit channels

PACKAGING AND YIELD

Five Star® Rapid Surface Repair Easy Mix is packaged in a .64 gal. (2.42 L) kit containing .32 gal. (1.21 L) "A", .32 gal. (1.21 L) "B" and 50 lbs. (22.7 kg) of aggregate yielding approximately .41 ft³ (.011 m³) per kit.

SHELF LIFE

One year in original unopened packaging when stored in dry conditions; high relative humidity and temperature will reduce shelf life.

**Traffic time dependent upon air and substrate temperature.*

TYPICAL PROPERTIES AT 77°F (25°C)

Mix Ratio by Volume	(1) Part A : (1) Part B
Viscosity @ 77°F (25°C) - mixed	60 cps
Gel Time, Neat	2 to 3 minutes
Working time with Aggregate	Approx. 5 minutes
Cured	
Color	Dark Grey
Cure Time (reopen to traffic)	30 minutes
Hardness, Durometer D, ASTM D-2240	70
Tensile Strength, ASTM D-412	3,000 psi (20.7 MPa)
Compressive Strength, ASTM C-579B	
1 hour	2,000 psi (13.8 MPa)
1 day	6,000 psi (41.3 MPa)
7 days	7,000 psi (48.2 MPa)
28 days	8,000 psi (55.1 MPa)
Elongation, ASTM D-638	10 - 15%
Bond Strength, ASTM C-882	2,000 psi (13.8 MPa)

The data shown above reflects typical results based on laboratory testing under controlled conditions. Reasonable variations from the data shown may result. Test methods are modified where applicable.

PLACEMENT GUIDELINES

SURFACE PREPARATION

1. Prepare concrete surfaces to a minimum CSP-4 (Concrete Surface Profile per ICRI Technical Standard 03732). Ensure surfaces are clean, sound and rough prior to repair.
2. For overlays, cut keyway channel (groove) using concrete saw equipped with dry cut diamond blade around perimeter of area to be resurfaced. Keyway channel (groove) depth shall be a minimum of 1/2 inch (12.7 mm). Surfaces adjacent to a vertical plane (such as curbs, walls, tanks, etc.) shall have keyway channels cut approximately 4 – 6 inches (101.6 - 152.3 mm) back from vertical plane towards the interior of area to be resurfaced. Keyway channel shall be 1/2 inch (12.7 mm) deep by 1/2 inch (12.7 mm) wide.
3. For overlays, chip 2 inch (50.8 mm) wide taper back from interior edge of keyway channel at all termination edges (i.e., drains, doors, etc.). Using bush hammer or chipping gun equipped with a 1 – 2 inch (25.4 - 50.8 mm) wide spade blade, chip a 2 inch (50.8 mm) wide taper back from edge of interior keyway channel (groove) inward towards the area being resurfaced. Taper shall match depth of keyway channel at its deepest point, which is the edge of the keyway, and taper out to 0 inches at its most shallow point, 2 inches (50.8 mm) towards the interior of the area to be resurfaced.
4. For crack filling, route out as necessary to a maximum 1/2 inch wide by 1/2 inch deep, minimum.
5. Vacuum dust and dirt from all surfaces.
6. Surfaces must be completely dry and free of moisture prior to installation.

MIXING INSTRUCTIONS: Mix ratio is 1:1 by volume. Mix a small sample and test prior to actual placement. Larger mix volumes can generate significant exotherm. Mix Components A & B thoroughly with drill and paddle for 30 seconds then add aggregate. Continue mixing for 30 seconds until aggregate is completely wetted.

NOTE: PRIOR TO APPLICATION, READ ALL PRODUCT PACKAGING THOROUGHLY. For more detailed placement procedures, refer to Five Star® Design-A-Spec™ installation guidelines or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

CLEAN-UP: Clean tools immediately after use with xylene or MEK.

CONSIDERATIONS

- Product should be stored at 50–80°F (10–27°C).
- Product may be installed between 0–100°F (-18–37°C). For temperatures above or below these limits please consult Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.
- Keep material out of sun or hot areas prior to applying, as this may cause working time to be diminished and could cause poor appearance and/or adhesion.

CAUTION

This product may cause skin and eye irritation. Do not inhale vapors. Provide adequate ventilation. Protect against contact with skin and eyes. Wear rubber gloves, long sleeve shirt, goggles with side shields. In case of contact with eyes, flush repeatedly with water and contact a physician. Areas of skin contact should be promptly washed with soap and water. Do not take internally. Keep product out of reach of children. **PRIOR TO USE, REFER TO SAFETY DATA SHEET.**

For worldwide availability, additional product information and technical support, contact your local Five Star® distributor, local sales representative, or call Five Star Products' Engineering and Technical Service Center at 1-800-243-2206.

SKU / PRODUCT CODE	DESCRIPTION	#UNITS/PALLET	UNIT SIZE
30928	Five Star® Rapid Surface Repair Easy Mix Kit	120	Resin (A): 0.32 gal (1.2 L) Hardener (B): 0.32 gal (1.2 L) Aggregate (C): 50 lb. (22.7 kg) bag

WARRANTY: "FIVE STAR PRODUCTS, INC. (FSP) PRODUCTS ARE MANUFACTURED TO BE FREE OF MANUFACTURING DEFECTS AND TO MEET FSP'S CURRENT PUBLISHED PHYSICAL PROPERTIES WHEN APPLIED IN ACCORDANCE WITH FSP'S DIRECTIONS AND TESTED IN ACCORDANCE WITH ASTM AND FSP STANDARDS. HOWEVER, SHOULD THERE BE DEFECTS OF MANUFACTURING OF ANY KIND, THE SOLE RIGHT OF THE USER WILL BE TO RETURN ALL MATERIALS ALLEGED TO BE DEFECTIVE, FREIGHT PREPAID TO FSP, FOR REPLACEMENT. THERE ARE NO OTHER WARRANTIES BY FSP OF ANY NATURE WHATSOEVER, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IN CONNECTION WITH THIS PRODUCT. FSP SHALL NOT BE LIABLE FOR DAMAGES OF ANY SORT, INCLUDING PUNITIVE, ACTUAL, REMOTE, OR CONSEQUENTIAL DAMAGES, RESULTING FROM ANY CLAIMS OF BREACH OF CONTRACT, BREACH OF ANY WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR FROM ANY OTHER CAUSE WHATSOEVER. FSP SHALL ALSO NOT BE RESPONSIBLE FOR USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT HELD BY OTHERS."

Five Star Products, Inc.
Corporate Headquarters
60 Parrott Drive
Shelton, CT 06484 USA
Tel: +1 203-336-7900 • Fax: +1 203-336-7930
FiveStarProducts.com

Specifications Subject to Change.

For most current version of datasheet, go to FiveStarProducts.com



© 2018 Five Star Products, Inc. | 07-19-2018
12512 Rev. H | American Owned & Operated

